

PITTSBURGH CORNING FOAMGLAS®

INSULATION ACCESSORIES

800 Presque Isle Drive
Pittsburgh, Pennsylvania 15239-2799
Tel: 724/327-6100 • 800/359-8433
Fax: 724-387-3807

www.foamglasinsulation.com

DESCRIPTION:

PITTCOTE® 404 coating is a highly flexible, acrylic latex coating used with FOAMGLAS® insulation where a superior weather barrier coating is required

PITTCOTE® 404 coating is available in colors and may be applied by glove, trowel, brush, or spray.

*TYPICAL PROPERTIES:

Color:	Bright White
Wt/gallon (lbs.):	11.25 – 11.5 (1.3 – 1.4)
Solids, wt %:	67
Elongation % (ASTM D-412)	≥ 200
**Coverage: gal/100 ft ² :	6 to 8
mils:	55 to 70
l/m ² :	2.5 to 3.3
Application Temp, °F (°C):	40 (4)
Service Tem °F (°C):	
Continuous:	-30 to 180 (-34 to 82)
Intermittent:	220 (104)
Solvent:	Water
Flash Point:	Non-Flammable
Flame Spread:	5
Smoke Development	10
ASTM E84	
Water Vapor Permeability, ASTM E96	
Procedure E, perm-in	0.4
perms @ 55 mils	7.27
perm-cm	0.16
***Drying Time, hrs:	Touch 3 Through 24

* Properties subject to change. Consult Pittsburgh Corning Corporation

** Allowance should be made for losses during application.

***Will vary with weather conditions and thickness.

SURFACE PREPARATION:

The FOAMGLAS® insulation surface should be dry, free of frost, oil and grease. Insulation should be fitted so the joints are tight and without broken or rounded corners. Any surface variations between blocks should be eliminated by rubbing the insulation smooth. Excess sealant or adhesive should be removed from the insulation surface. Inside corners should be canted and outside corners rounded.

PITTCOTE® 404 COATING PRODUCT DATA SHEET

IMPORTANT: MATERIAL SAFETY DATA SHEETS ARE AVAILABLE AND SHOULD BE READ BEFORE USING THIS PRODUCT.

Blasting of all adjacent surfaces should be completed and metal primed before insulation is coated.

MATERIAL PREPARATION:

Stir well before using. May be thinned 5% with clean water. Store above 32°C (0°C).

APPLICATION:

See **CAUTION:** PITTCOTE® 404 coating can be applied by glove, trowel, brush or spray. Spray equipment should be checked before application.

Apply tack coat of 3-4 gal./100 ft² (1.2-1.6 l/m²). Immediately embed reinforcing fabric PC® Fabric 79 (FI-159), lapping fabric a minimum of 3-4 inches (7.5-10 cm), When first coat has dried, apply second coat of 3-4 gal./100ft². Fabric outline will be faintly visible when dry. Inspect and touch up as needed.

On interior building insulation, reinforcing may be eliminated in some cases.

Spray application recommendations are a 30:1 ratio or larger pump with a ½" to ¾" diameter high pressure hose. The orifice of the spray tip should be 0.035" to 0.045". A reversible tip is recommended. Use a squeegee to press coating into surface.

CLEAN UP:

Clean equipment and spills with water before coating dries.

LIMITATIONS;

Protect from **FREEZING**. STORE and ship above 32°F (0°C). Do not use where water will pond.

Do not apply if rain or temperatures below 40°F (4°C) are expected before coating dries.

PACKAGING:

5 gallon containers
55 gallon containers

CAUTION:

This material is intended to be used only with FOAMGLAS® insulation and in conformity with Pittsburgh Corning's standard instructions. Be sure you have read and understand all instructions and Material Safety Data Sheets before using. Material Safety Data Sheets should be considered part of this product data sheet.

INGREDIENTS:

	CAS #
Acrylic polymer emulsion	29129-78-0
Hydrated Alumina	21645-51-2
Water	7732-18-5
Calcium Carbonate	1317-65-3
Titanium Dioxide	13463-67-7

IRRITANT:

Irritation to eyes, skin and respiratory system may occur upon prolonged and repeated exposure. Avoid prolonged and repeated contact with skin. Wear protective gloves. Wash hands after use. Do not breathe sprayed particles. When spraying, wear a paint particulate mask. Avoid contact with eyes. Wear eye protection.

FIRE HAZARD CLASSIFICATION:

Health: 1 Fire: 0 Reactivity: 0

HARMFUL OR FATAL IF SWALLOWED**KEEP OUT OF REACH OF CHILDREN**

This material is designed for application only by professional, trained personnel using proper equipment and is not intended for sale to the general public.

The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning Corporation has no control over installation workmanship, accessory materials or conditions of application, NO EXPRESS OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE as to the performance of an installation containing Pittsburgh Corning products. In no event shall Pittsburgh Corning be liable for any damages arising because of product failure, whether incidental, special, consequential or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning Corporation provides written warranties for many of its products, and such warranties take precedence over the statements contained herein.